

A701 OB E A SRC



DESCRIPTION	NORM EN ISO 20347:2012	RESULT	REQUIREMENT
UPPER: pierced microfiber	5.4.3 Tear strength	98 N	≥60 N
	5.4.6 Water vapor permeability Coefficient	2,0 mg/cm ² h 18,2 mg/cm ²	≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
VAMP LINING: breathable, antibacterial, abrasion resistance textile	5.5.1 Tear strength	43 N	≥ 15 N
	5.5.2 Abrasion resistance(Wet) Abrasion resistance(Dry)	No holes No holes	25.600 cycles 12.800 cycles
	5.5.3 Water vapor permeability Coefficient	4,3 mg/cm ² h 35,3 mg/cm ²	≥ 2,0 mg/(cm ² h) ≥20,0 mg/cm ²
QUARTER LINING: breathable, antibacterial, abrasion resistance textile	5.5.1 Tear strength	43 N	≥ 15 N
	5.5.2 Abrasion resistance(Wet) Abrasion resistance(Dry)	No holes No holes	25.600 cycles 12.800 cycles
	5.5.3 Water vapor permeability Coefficient	4,3 mg/cm ² h 35,3 mg/cm ²	≥ 2,0 mg/(cm ² h) ≥20,0 mg/cm ²
FOOTBED: Removable, cushioned, antistatic insole.	5.7.4.2 Abrasion resistance (Wet) Abrasion resistance(Dry)	No holes No holes	25.600 cycles 12.800 cycles
	OUTSOLE: PU 1D, antislip SRC	5.8.2 Tear strength 5.8.3 Abrasion resistance 5.8.4 Flexing resistance 5.8.5 Hydrolisis 6.4.2 Oils resistance 5.11 Pressed ceramic tile floor on detergent resistance Flat slip Heel slip Stainless steel plate on glycerin resistance Flat slip Heel slip	7 kN/m 172 mm ³ 3 mm 4,0 mm 0,5 % 0,43 0,35 0,22 0,16

SIZES : 35-47