

A703 OB E A FO SRC



DESCRIPTION	NORM EN ISO 20345:2011	RESULT	REQUIREMENT	
UPPER: Microfiber	5.4.3 Tear strength	102 N	≥60 N	
	5.4.6 Water vapor permeability Coefficient	1,6 mg/cm ² h 16,6 mg/cm ²	≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²	
VAMP LINING: breathable, antibacterial, abrasion resistance textile	5.5.1 Tear strength	30 N	≥ 15 N	
	5.5.2 Abrasion resistance (Wet) Abrasion resistance (Dry)	No holes No holes	25.600 cycles 12.800 cycles	
	5.5.3 Water vapor permeability Coefficient	4,4 mg/cm ² h 37,9 mg/cm ²	≥ 2,0 mg/(cm ² h) ≥20,0 mg/cm ²	
FOOTBED: Removable, cushioned, antistatic insole.	5.7.4.2 Abrasion resistance (Wet) Abrasion resistance (Dry)	No holes No holes	25.600 cycles 12.800 cycles	
	OUTSOLE: PU 1D, antislip SRC	5.8.2 Tear strength	7 kN/m	≥ 5 kN/m
5.8.3 Abrasion resistance		172 mm ³	≤ 250 mm ³	
5.8.4 Flexing resistance		3 mm	≤ 4,0 mm	
5.8.5 Hydrolisis		4,0 mm	≤ 6,0 mm	
6.4.2 Oils resistance		0,5 %	≤ 12%	
5.11 Pressed ceramic tile floor on detergent resistance				
Flat slip		0,43	≥ 0,32	
Heel slip	0,35	≥ 0,28		
Stainless steel plate on glycerin resistance				
Flat slip	0,22	≥ 0,18		
Heel slip	0,16	≥ 0,13		

SIZES : 35-47