

## D203 O1 FO SRC



DESCRIPTION	NORM EN ISO 20347:2012	RESULT	REQUIREMENT
<b>UPPER:</b> pierced microfiber	5.4.3 Tear strength	102 N	≥60 N
	5.4.6 Water vapor permeability	1,6 mg/cm <sup>2</sup> h	≥ 0,8 mg/cm <sup>2</sup> h
	Coefficient	16,6 mg/cm <sup>2</sup>	≥ 15,0 mg/cm <sup>2</sup>
<b>VAMP LINING:</b> breathable, antibacterial, abrasion resistance textile	5.5.1 Tear strength	30 N	≥ 15 N
	5.5.2 Abrasion resistance(Wet)	No fori	25.600 cycles
	Abrasion resistance(Dry)	No fori	12.800 cycles
<b>QUARTER LINING:</b> breathable, antibacterial, abrasion resistance textile	5.5.3 Water vapor permeability	4,4 mg/cm <sup>2</sup> h	≥ 2,0 mg/(cm <sup>2</sup> h)
	Coefficient	37,9 mg/cm <sup>2</sup>	≥20,0 mg/cm <sup>2</sup>
	5.5.1 Tear strength	30 N	≥ 15 N
<b>FOOTBED:</b> Removable, cushioned, antistatic insole.	5.5.2 Abrasion resistance(Wet)	No fori	25.600 cycles
	Abrasion resistance(Dry)	No fori	12.800 cycles
	5.5.3 Water vapor permeability	4,4 mg/cm <sup>2</sup> h	≥ 2,0 mg/(cm <sup>2</sup> h)
<b>OUTSOLE:</b> PU 1D, antislip SRC	Coefficient	37,9 mg/cm <sup>2</sup>	≥20,0 mg/cm <sup>2</sup>
	5.7.4.2 Abrasion resistance (Wet)	No holes	25.600 cycles
	Abrasion resistance(Dry)	No holes	12.800 cycles
<b>OUTSOLE:</b> PU 1D, antislip SRC	5.8.2 Tear strength	7 kN/m	≥ 5 kN/m
	5.8.3 Abrasion resistance	172 mm <sup>3</sup>	≤ 250 mm <sup>3</sup>
	5.8.4 Flexing resistance	3 mm	≤ 4,0 mm
	5.8.5 Hydrolisis	4,0 mm	≤ 6,0 mm
	6.4.2 Oils resistance	0,5 %	≤ 12%
	5.11 Pressed ceramic tile floor on detergent resistance		
	Flat slip	0,43	≥ 0,32
	Heel slip	0,35	≥ 0,28
	Stainless steel plate on glycerin resistance		
	Flat slip	0,22	≥ 0,18
	Heel slip	0,16	≥ 0,13

**SIZES : 35-47**