

E103 OB E A ESD SRC



DESCRIPTION	NORM EN ISO 20347:2012	RESULT	REQUIREMENT
UPPER: Microfiber	5.4.3 Tear strength	102 N	≥60 N
	5.4.6 Water vapor permeability	1,6 mg/cm ² h	≥ 0,8 mg/cm ² h
	Coefficient	16,6 mg/cm ²	≥ 15,0 mg/cm ²
VAMP LINING: breathable, antibacterial, abrasion resistance textile	5.5.1 Tear strength	45 N	≥ 15 N
	5.5.2 Abrasion resistance (Wet)	No fori	25.600 cycles
	Abrasion resistance (Dry)	No fori	12.800 cycles
	5.5.3 Water vapor permeability	4,5 mg/cm ² h	≥ 2,0 mg/(cm ² h)
FOOTBED: Removable, cushioned, antistatic insole.	5.7.4.2 Abrasion resistance (Wet)	No holes	25.600 cycles
	Abrasion resistance (Dry)	No holes	12.800 cycles
	OUTSOLE: PU 1D, antislip SRC	5.8.2 Tear strength	7 kN/m
5.8.3 Abrasion resistance		172 mm ³	≤ 250 mm ³
5.8.4 Flexing resistance		3 mm	≤ 4,0 mm
5.8.5 Hydrolisis		4,0 mm	≤ 6,0 mm
6.4.2 Oils resistance		0,5 %	≤ 12%
5.11 Pressed ceramic tile floor on detergent resistance			
Flat slip		0,43	≥ 0,32
Heel slip		0,35	≥ 0,28
Stainless steel plate on glycerin resistance			
Flat slip		0,22	≥ 0,18
Heel slip	0,16	≥ 0,13	

SIZES : 35-47

EXENA S.r.l.

Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

C.F. e P. IVA: 01336080435 – Reg.Imprese MC n.01336080435 – REA MC144207

www.exena.it – info@exena.it – pec: amministrazione@pec.exena.it