

P303 01 FO SRC



DESCRIPTION	NORMA EN ISO 20347:2012	RESULT	REQUIREMENT
UPPER: Breathable microfiber	5.4.3 Tear strength	102 N	≥60 N
	5.4.6 Water vapor permeability	1,6 mg/cm ² h	≥ 0,8 mg/cm ² h
	Coefficient	16,6 mg/cm ²	≥ 15,0 mg/cm ²
VAMP LINING: Breathable, antibacterial, abrasion resistance	5.5.1 Tear strength	30 N	≥ 15 N
	5.5.2 Abrasion resistance(Wet)	No fori	25.600 cycles
	Abrasion resistance(Dry)	No fori	12.800 cycles
QUARTER LINING: Breathable, antibacterial, abrasion resistance	5.5.3 Water vapor permeability	4,4 mg/cm ² h	≥ 2,0 mg/(cm ² h)
	Coefficient	37,9 mg/cm ²	≥20,0 mg/cm ²
	5.5.1 Tear strength	30 N	≥ 15 N
FOOTBED: Removable, cushioned, antistatic insole	5.5.2 Abrasion resistance(Wet)	No fori	51.200 cycles
	Abrasion resistance(Dry)	No fori	25.600 cycles
	5.5.3 Water vapor permeability	4,4 mg/cm ² h	≥ 2,0 mg/(cm ² h)
OUTSOLE PU 1D SRC, antislip	Coefficient	37,9 mg/cm ²	≥20,0 mg/cm ²
	5.7.4.2 Abrasion resistance(Wet)	No holes	25.600 cycles
	Abrasion resistance(Dry)	No holes	12.800 cycles
	5.8.2 Tear strength	7 kN/m	≥ 5 kN/m
	5.8.3 Abrasion resistance	172 mm ³	≤ 250 mm ³
	5.8.4 Flexing resistance	3 mm	≤ 4,0 mm
	6.4.2 Oils resistance	4,0 mm	≤ 12%
	5.11 Pressed ceramic tile floor on detergent resistance	0,5 %	
	Flat slip		≥ 0,32
	Heel slip	0,43	≥ 0,28
	Stainless steel plate on glycerin resistance	0,35	
Flat slip		≥ 0,18	
Heel slip	0,22	≥ 0,13	
		0,16	

MISURE : 35- 47